

L5 ANSWER 122 OF 575 CA COPYRIGHT 2004 ACS on STN
 AN 132:211720 CA
 ED Entered STN: 07 Apr 2000
 TI Manufacture of light-weight hollow wallboard with high strength and low production cost
 IN Wan, Yunzhong
 PA Loading and Unloading Service Co., Neijiang Vehicle Section, Peop. Rep. China
 SO Faming Zhuanli Shenqing Gongkai Shuomingshu, 4 pp.
 CODEN: CNXXEV
 DT Patent
 LA Chinese
 IC ICM C04B020-00
 CC 58-4 (Cement, Concrete, and Related Building Materials)
 FAN.CNT 1

	PATENT NO.	KIND	DATE	APPLICATION NO.	DATE
PI	CN 1178202	A	19980408	CN 1997-107756	19971103
PRAI	CN 1997-107756		19971103		

AB The wallboard is prepd. from cement 45-55, expanded material 10-15, fly ash 30-35, gypsum 4-7, water 40-55 wt.%, and glass fiber. The manuf. process comprises: mixing cement with gypsum and fly ash, adding expanded material under stirring, mixing with water to obtain a micro-foamed slurry (450-560 kg/m3), pouring the slurry into a mold, laying a layer of glass fiber, putting a mold core into the mold, adding slurry to 2/3 designed thickness, laying another layer of glass fiber, adding slurry to designed thickness, settling for 1-1.5 h, removing the mold core, de-molding after 4 h, and curing. Preferably, the expanded material is expanded vermiculite or perlite;.

ST light wt hollow wallboard strength prodn cost; cement light wt hollow wallboard; expanded vermiculite light wt hollow wallboard; expanded perlite light wt hollow wallboard; fly ash gypsum glass fiber wallboard; gypsum fly ash glass fiber wallboard; glass fiber fly ash gypsum wallboard

IT Perlite
 RL: PEP (Physical, engineering or chemical process); TEM (Technica